# **SEE Testing of the RH1013 Dual Precision Operational Amplifier**

Ray Ladbury (NASA/GSFC) &
&
Stephen Buchner (QSS Group Inc)

Texas A&M Cyclotron Facility December 2005

#### Introduction

The RH1013, manufactured by Linear Technology, was tested for Single Event Effects (SEEs) at Texas A&M Cyclotron Facility (TAMU) in December 2005. The RH1013 consists of two operational amplifiers in a 10-pin flatpack. The part is expected to be sensitive to single event transients (SETs). The object of the test was to determine the maximum amplitude and width of the SETs.

## **Part Identification**

One part was tested. The following identification information is on the lid:

RH1013 Q 0343A

Figure 1 shows the connections to the RH1013.




Fig. 1. Pinout for the RH1013

## **Test Method**

One part was de-lidded and mounted on a board. One of the two op-amps (a) was connected with a gain of 10. The other (b) was configured as either a voltage follower or an amplifier with gain of 2 using a jumper. The supply was +/- 15V. The part was located in front of the exit port of the accelerator and was controlled remotely through a LAN.

Both positive and negative transients were captured on an oscilloscope (11 pF) oscilloscope probes to the output (Pin 1) of the RH1013. The trigger levels were set at +100 mV and -100 mV.

#### **lons Used**

Ion	Energy (MeV)	LET (MeV.cm <sup>2</sup> /mg)
Ar	15	8.57
Kr	15	28.8
Xe	15	53.1

# **Results**

The captured transients had a variety of amplitudes and widths. Fig. 2 is a plot of amplitude vs width at an effective LET of 75 MeV.cm<sup>2</sup>/mg obtained by rotating the device so that the ion beam was incident at an angle of  $45^{\circ}$ . There are both positive and negative transients when the input is 0.5 V. The longest transients had widths of < 5  $\mu$ s. Fig. 3 shows the same plot for transients produced by ions with LET of 53.1 MeV.cm<sup>2</sup>/mg. All those transients had widths less than 1  $\mu$ s. Fig. 4 shows the SET cross-section as a function of effective LET for transients with amplitudes larger than +/-100 mV. Fig. 3 and Fig. 4 show the same data for different configurations.




Fig. 2. Plot of amplitude vs width for the RH1013 configured as a voltage follower and exposed to 15 MeV Xe ions (LET of 75 MeV.cm<sup>2</sup>/mg at  $45^{\circ}$ ). The largest transients have amplitudes of -6V and widths of  $20 \,\mu s$ .




Fig. 3. Plot of amplitude vs width for transients in the RH1013 configured as an amplifier with gain of 2. The ions were 15 MeV Xe ions (Effective LET = 75 MeV.cm<sup>2</sup>/mg at 45°). The largest transients had amplitudes of 4 V and widths of 15  $\mu$  s.




Fig. 4. Plot of amplitude vs width for SETs produced with 15 MeV Xe ions (LET = 75 MeV.cm<sup>2</sup>/mg at 45°). The longest transients had amplitudes of +5V and widths of 17  $\mu$ s.

The cross-section was also calculated for the different gains. They are displayed in Figs. 5, 6, and 7.




Fig. 5. Plot of Transient Cross-Section vs LET for Gain=1.




Fig. 6. Plot of Transient Cross-Section vs LET for Gain=2.

### 1.00E-01 Cross-section (cm<sup>2</sup>/device) 1.00E-02 1.00E-03 1.00E-04 1.00E-05 1.00E-06 10 0 20 30 40 50 60 70 80 LET [MeV.cm<sup>2</sup>/mg)]

RH1013 Gain=10

Fig. 7. Plot of Transient Cross-Section vs LET for Gain=10.

No destructive single event effects occurred up to a LET of 75 MeV.cm<sup>2</sup>/mg. Also, no latchup was observed.

# Category

In general, devices are categorized based on heavy ion test data into one of the four following categories:

- Category 1 Recommended for use in all NASA/GSFC spaceflight applications.
- Category 2 Recommended for use in NASA/GSFC spaceflight applications, but may require mitigation techniques.
- Category 3 Recommended for use in some NASA/GSFC spaceflight applications, but requires extensive mitigation techniques or hard failure recovery mode.
- Category 4 Not recommended for use in any NASA/GSFC spaceflight applications.

Based on results of proton testing and previous heavy ion data, this part is assigned to category 2.